

SACi900 8x30

Coal based activated carbon produced by high temperature steam activation. It complies with the European Standard EN-12915.

Technical details	5% max 90% min 5% max	+8 ASTM 8x30 ASTM -30 ASTM	+2.36mm 2.36-0.60mm -0.60mm
Particle Size (ASTM D2862)			
Apparent Density, Dry (ASTM D2854)	520-560 kg/m ³		
Iodine Number (AWWA B604)	900 mg/g min		
Ash (ASTM D2866)	15% max		
Moisture Content (ASTM D2867)	5% max (as packed)		
Water soluble content	0.5% max		
Hardness Number (ASTM D3802)	90 min		